



## Technical Data Sheet

<b>ARCO MOR 30</b>		
<b>Product Description</b>	<b>Fireclay Mortar</b>	
<b>Raw material basis</b>	<b>Fireclay</b>	
<b>Chemical Analysis (%):</b>		
Al <sub>2</sub> O <sub>3</sub>	%	29-30
SiO <sub>2</sub>	%	58-59
Fe <sub>2</sub> O <sub>3</sub>	%	2.5-3.5
TiO <sub>2</sub>	%	3.5-4.5
K <sub>2</sub> O+Na <sub>2</sub> O	%	≤1.0
MgO+CaO	%	≤1.5
<b>Physical Properties:</b>		
Refractoriness	°C	1625
PLC at Service Limit	%	-0.2
Service Limit	°C	1225
Grain size	mm	0-0.1
Approximate amount of water required	%	10-12

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.  
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.