



Technical Data Sheet

ARCO MOR 35		
Product Description	Fireclay Mortar	
Raw material basis	Fireclay	
Chemical Analysis (%):		
Al ₂ O ₃	%	34-36
SiO ₂	%	54-55
Fe ₂ O ₃	%	2.0-3.0
TiO ₂	%	3.5-4.5
K ₂ O+Na ₂ O	%	≤0.7
MgO+CaO	%	≤1.2
Physical Properties:		
Refractoriness	°C	1650
PLC at Service Limit	%	-1.8
Service Limit	°C	1275
Grain size	mm	0-0.1
Approximate amount of water required	%	10-12

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.