



Technical Data Sheet

ARCO MOR 80		
Product Description	High Alumina Mortar	
Raw material basis	Bauxite	
Chemical Analysis (%):		
Al ₂ O ₃	%	78-80
SiO ₂	%	16-17
Fe ₂ O ₃	%	0.5-1.0
TiO ₂	%	1.0-1.5
K ₂ O+Na ₂ O	%	≤0.2
MgO + CaO	%	≤0.5
Physical Properties:		
Refractoriness	°C	1870
PLC at Service Limit	%	-1.0
Service Limit	°C	1500
Grain size	mm	0-0.1
Approximate amount of water required	%	9-11

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.