



Technical Data Sheet

| ARCO RAM - 30 | | |
|---|--------------------|-----------|
| Product Description | Ramming Mix | |
| Raw material basis | Fireclay | |
| Chemical Analysis (%): | | |
| Al ₂ O ₃ | % | 30-32 |
| SiO ₂ | % | 56-58 |
| Fe ₂ O ₃ | % | 3.5-4.5 |
| TiO ₂ | % | 4.5-5.5 |
| Physical Properties: | | |
| Bulk density after drying at | Kg/m ³ | 1900-2000 |
| Cold Crushing Strength(C.C.S) after at Max Service Temperature (°c) | Kg/cm ² | 300-400 |
| Max Service Temperature | °C | 1200 |
| Grain size | mm | 0-6 |
| Approximate amount of water required | % | 4.5-5.5 |

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.