



Technical Data Sheet

ARCO RAM - 40		
Product Description	Ramming Mix	
Raw material basis	Fireclay	
Chemical Analysis (%):		
Al ₂ O ₃	%	40-42
SiO ₂	%	48-50
Fe ₂ O ₃	%	3.5-4.5
TiO ₂	%	4.5-5.5
Physical Properties:		
Bulk density after drying at	Kg/m ³	1900-2000
Cold Crushing Strength(C.C.S) after at Max Service Temperature (°c)	Kg/cm ²	350-450
Max Service Temperature	°C	1275
Grain size	mm	0-6
Approximate amount of water required	%	4.5-5.5

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.