



Technical Data Sheet

ARCO RAM - 60		
Product Description	Ramming Mix	
Raw material basis	Fireclay	
Chemical Analysis (%):		
Al ₂ O ₃	%	59-61
SiO ₂	%	29-31
Fe ₂ O ₃	%	2.5-3.5
TiO ₂	%	4.0-5.0
Physical Properties:		
Bulk density after drying at	Kg/m³	2000-2100
Cold Crushing Strength(C.C.S) after at Max Service Temperature (°c)	Kg/cm²	400-500
Max Service Temperature	°C	1400
Grain size	mm	0-6
Approximate amount of water required	%	4.5-5.5

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.