



Technical Data Sheet

ARCO RAM - 85		
Product Description	Ramming Mix	
Raw material basis	Bauxite	
Chemical Analysis (%):		
Al ₂ O ₃	%	83-85
SiO ₂	%	8-10
Fe ₂ O ₃	%	2.0-3.0
TiO ₂	%	3.0-4.0
Physical Properties:		
Bulk density after drying at	Kg/m³	2450-2550
Cold Crushing Strength(C.C.S) after at Max Service Temperature (°c)	Kg/cm²	500-600
Max Service Temperature	°C	1620
Grain size	mm	0-6
Approximate amount of water required	%	4.0-4.5

- Packing in 25 Kg Bags.
- Note: The above technical information are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.
Rev.Date:2016/14/09
- This specifications can be changed according to customer requirement and order.

مشخصات فوق بر اساس نیاز و سفارش مشتریان قابل تغییر است.